International Journal for Multidisciplinary Research (IJFMR)
E-ISSN: 2582-2160 ● Website: www.ijfmr.com ● Email: editor@ijfmr.com

Osseointegration: Biological Basis, Materials Science, and Clinical Perspectives in Dental Implantology

Dr. Gaurav Gupta[1], Dr. Shaveta Bansal[2], Dr. Sajjy Upinder[3], Dr. Shailaja Kapila[4]

[1]Professor and Head of Department, Prosthodontics and Crown & Bridge, Guru Nanak Dev Dental College And Research Institute Sunam
[2]Professor, Prosthodontics and Crown & Bridge, Guru Nanak Dev Dental College And Research Institute Sunam
[3]Reader, Prosthodontics and Crown & Bridge, Guru Nanak Dev Dental College And Research Institute Sunam
[4]PG student, Prosthodontics and Crown & Bridge, Guru Nanak Dev Dental College And Research Institute Sunam

Abstract

Osseointegration is defined as the direct, structural, and functional connection between living bone and the surface of a load-bearing implant at the light microscopic level. Initially observed by Brånemark in the 1950s, it has become the fundamental principle governing the long-term stability of endosseous dental implants. This process involves a cascade of complex biological and biomechanical interactions that lead to bone anchorage of metallic surfaces without the formation of intervening fibrous tissue. The predictability of osseointegration depends on multiple factors, including implant surface chemistry, roughness, host bone quality, and the molecular events driving osteogenesis. Recent advancements in nanotechnology, surface modification, and biomimetic coatings have further refined this phenomenon, enabling rapid bone apposition and enhanced mechanical fixation. This article reviews the historical context, fundamental biological mechanisms, and scientific evolution of osseointegration, establishing the foundation for its clinical application in contemporary implant dentistry.



1. Introduction

The success of dental implant therapy is primarily dependent on the process of osseointegration, which enables stable anchorage of implants within alveolar bone. The term was first introduced to describe the direct structural connection between titanium and living bone, characterized by intimate bone contact observable under light microscopy. In the past five decades, the concept of osseointegration has evolved from a biological curiosity into a cornerstone of reconstructive dental science. Current research recognizes osseointegration not as a passive process but as an active, dynamic interaction between the host tissue and the implant biomaterial, mediated through cellular and molecular signaling pathways [1,2].

The clinical predictability of osseointegration has transformed dental practice by providing a reliable alternative to conventional prosthodontics. The fundamental principle lies in achieving mechanical stability initially, followed by biological fixation through bone remodeling and mineralized tissue deposition. This transition from primary to secondary stability is influenced by surgical precision, implant macrodesign, and the biological environment of the host bone [3]. Advances in digital technology, biomaterials, and regenerative medicine continue to expand the possibilities for optimizing osseointegration outcomes.

2. Historical Overview

The origins of osseointegration trace back to the experimental observations of Professor Per-Ingvar Brånemark in the mid-20th century. While conducting studies on microcirculation in rabbit bone using titanium optical chambers, Brånemark observed that the chambers became irreversibly fused to the host bone tissue [4]. This unexpected finding led to the recognition that titanium possessed unique biological properties conducive to bone integration. Brånemark's subsequent investigations culminated in the first

successful clinical application of titanium dental implants in the 1960s, marking a revolutionary shift in restorative dentistry [5].

The concept was further developed through extensive experimental and clinical research in the 1970s and 1980s. Albrektsson and colleagues established the essential parameters for achieving successful osseointegration, including biocompatibility, mechanical stability, controlled load distribution, and the absence of excessive micromotion at the interface [6]. This foundational work defined the biomechanical and biological prerequisites that remain central to implantology today.

Subsequent decades witnessed continuous refinement in implant design and surface technology. Early machined titanium surfaces gave way to micro-roughened, sandblasted, and acid-etched designs that enhanced bone-to-implant contact (BIC). These advancements improved both the rate and quality of osseointegration, enabling immediate and early loading protocols. The introduction of nanostructured and chemically modified surfaces in the 21st century further accelerated osseointegration kinetics, laying the groundwork for modern implant success [7,8].

4. Biology of Osseointegration

Osseointegration is a dynamic, multifactorial biological process characterized by direct bone apposition on the surface of an endosseous implant. The healing cascade involves an orchestrated sequence of inflammatory, proliferative, and remodeling events that mirror physiological bone repair [1,2]. Following implant placement, a blood clot forms, acting as a provisional matrix that recruits inflammatory cells and osteoprogenitors. Angiogenesis rapidly establishes a vascular network essential for the delivery of oxygen, nutrients, and signaling molecules. Over subsequent weeks, woven bone forms through intramembranous ossification, which later remodels into mature lamellar bone in close contact with the implant surface.

5. Molecular and Cellular Mechanisms

Osseointegration is mediated by a complex molecular dialogue between the implant surface and host tissue. Osteoblasts adhere to titanium oxide via integrin-mediated focal adhesions, initiating cytoskeletal reorganization and extracellular matrix deposition [3,4]. Osteoclasts play a complementary role, remodeling immature bone and regulating turnover. Key growth factors such as TGF-β, BMP-2, PDGF, and VEGF orchestrate angiogenesis and osteogenesis. This process is tightly regulated at the gene expression level through signaling pathways including Wnt/β-catenin, MAPK, and BMP-Smad.



6. Biomechanical Aspects

From a biomechanical perspective, osseointegration progresses from primary stability—achieved at implant placement—to secondary stability mediated by bone remodeling. Primary stability arises from mechanical interlocking between the implant threads and cortical bone, whereas secondary stability results from de novo bone formation at the interface [5,6]. Excessive micromotion (>150 μm) can disrupt this process, leading to fibrous encapsulation rather than bone bonding. Optimal load transfer is essential to stimulate bone remodeling through mechanotransduction.



7. Implant Materials

Titanium and its alloys remain the gold standard for dental implant fabrication due to their excellent biocompatibility, corrosion resistance, and mechanical properties. Commercially pure titanium (Grade IV) and titanium-aluminum-vanadium alloys (Ti-6Al-4V) exhibit high fatigue strength and form a stable oxide layer conducive to osseointegration [7]. Zirconia implants have emerged as a metal-free alternative, demonstrating favorable soft tissue response and aesthetic advantages. Material selection profoundly influences surface energy, protein adsorption, and subsequent cell adhesion.

Table 1. Physical and chemical properties of commonly used dental implant materials.



8. Surface Engineering and Modification

Surface modification is a pivotal determinant of osseointegration kinetics. Techniques such as sandblasting and acid-etching (SLA), anodization, laser texturing, and plasma spraying modify surface roughness and chemistry, enhancing osteoblast adhesion [8,9]. Nanostructured surfaces further increase surface energy and wettability, promoting rapid protein adsorption and bone apposition.

9. Bone–Implant Interface Chemistry

The interface between the implant surface and bone is governed by complex physicochemical interactions. The native titanium oxide layer (TiO2) spontaneously forms upon exposure to oxygen, creating a chemically stable and bioactive surface [10]. Protein adsorption occurs within seconds, mediated by van der Waals forces and hydrogen bonding, followed by integrin-mediated cellular attachment. Surface contamination and microgap formation can compromise this process, leading to impaired osseointegration.



10. Role of Nanotechnology

Nanotechnology offers unprecedented control over implant surface architecture, enabling the fabrication of nanoscale features that mimic the natural extracellular matrix. Titanium dioxide nanotubes, nanopatterned surfaces, and nano-hydroxyapatite coatings enhance osteoblast differentiation and accelerate bone bonding [11,12]. These modifications increase surface energy, improve wettability, and stimulate early cellular responses critical to rapid osseointegration



11. Bioactive and Biomimetic Coatings

Bioactive coatings have emerged as a strategic innovation to accelerate osseointegration by enhancing osteoconductivity and biochemical bonding at the implant interface. Among these, calcium phosphate (CaP) and hydroxyapatite (HA) coatings have been widely utilized due to their compositional similarity

to natural bone mineral [1,2]. These coatings facilitate ionic exchange, protein adsorption, and the recruitment of osteoprogenitor cells, thereby expediting bone apposition. Plasma-sprayed HA coatings, although effective, suffer from variable crystallinity and potential delamination; thus, contemporary research has shifted toward sol–gel, biomimetic, and electrophoretic deposition techniques offering superior adhesion and structural control.

Biomimetic coatings extend this concept further by incorporating organic components such as collagen, peptides (e.g., RGD sequences), and extracellular matrix (ECM) proteins. These materials mimic the native bone microenvironment, promoting integrin-mediated osteoblast adhesion and differentiation [3]. Recent developments in peptide-functionalized and growth-factor-releasing coatings have demonstrated enhanced osseointegration kinetics and improved long-term stability under functional loading.

12. 3D Printing and Additive Manufacturing

The advent of additive manufacturing (AM) has revolutionized implant design by enabling precise control over geometry, porosity, and surface architecture. Techniques such as selective laser melting (SLM) and electron beam melting (EBM) allow the fabrication of titanium implants with complex lattice structures that mimic trabecular bone morphology [4]. Such porous architectures not only reduce stiffness mismatch between the implant and bone but also promote vascularization and mechanical interlocking, leading to superior osseointegration performance.

AM technology further facilitates patient-specific implant fabrication, allowing the customization of macrodesign parameters such as thread pitch, taper, and diameter. Computational modeling and finite element analysis (FEA) play a critical role in optimizing load transfer characteristics and minimizing stress shielding [5]. Hybrid approaches combining AM with bioactive surface coatings represent a major step toward next-generation, functionally graded dental implants.

13. Digital Implant Design and CAD/CAM

Computer-aided design and computer-aided manufacturing (CAD/CAM) technologies have transformed implant dentistry by integrating digital precision into every stage of treatment planning and fabrication. Intraoral scanning and cone-beam computed tomography (CBCT) enable accurate assessment of bone morphology, guiding virtual implant placement that ensures optimal orientation relative to anatomical structures [6,7]. CAD/CAM workflows allow the production of custom abutments, surgical guides, and implant-supported prostheses with micron-level precision.

Digital workflows minimize human error and reduce chairside time, while computer-guided surgery enhances surgical accuracy and primary stability outcomes. Integration with finite element modeling allows preoperative simulation of stress distribution within peri-implant bone, predicting long-term performance under functional loads [8]. Artificial intelligence (AI)-driven CAD platforms are now being developed to automate implant selection and alignment, representing the next frontier in digital osseointegration.

14. Clinical Principles in Dental Implantology

Successful osseointegration in dental implantology relies on a comprehensive understanding of surgical precision, prosthetic planning, and patient-specific biological variables. Optimal implant placement requires meticulous three-dimensional positioning within the alveolar ridge to achieve proper load distribution and aesthetic integration. Key clinical determinants include bone quality, implant

macrogeometry, and surgical torque values [1,2]. Primary stability achieved during placement serves as the mechanical foundation upon which biological stability is developed.



15. Immediate and Delayed Loading Concepts

Implant loading protocols have evolved to accommodate both biological healing principles and patient-centered outcomes. Traditional delayed loading (3–6 months) allows complete bone maturation before functional loading, minimizing micromotion risk [3]. In contrast, immediate and early loading approaches capitalize on high initial stability and controlled occlusal forces to expedite rehabilitation. Success depends on achieving insertion torque >35 Ncm and resonance frequency analysis (RFA) values >70 ISQ, indicating adequate primary stability.

16. Surgical Techniques Enhancing Osseointegration

Minimally invasive surgical techniques contribute to improved osseointegration outcomes by preserving vascular integrity and minimizing thermal trauma. Critical parameters include drilling speed (<2000 rpm), continuous irrigation, and atraumatic insertion [4,5]. Guided surgery using computer-generated templates ensures precise implant angulation and depth control, optimizing biomechanical load distribution.

Subcrestal implant placement and ridge preservation protocols have been shown to enhance marginal bone retention. Additionally, the use of piezosurgical devices provides microvibration-based bone cutting, reducing thermal damage and promoting faster healing.

17. Peri-implant Bone Healing and Remodeling

Bone healing around implants is a dynamic and continuous process involving simultaneous resorption and apposition. Initially, woven bone forms directly on the implant surface through intramembranous ossification. Subsequent remodeling replaces this immature bone with organized lamellar bone exhibiting improved mechanical competence [6]. Osteocytes embedded within the bone matrix serve as mechanosensors, regulating bone turnover in response to mechanical loading.



18. Mechanical Stability and Micromotion

Mechanical stability determines the early success of osseointegration by ensuring intimate contact between bone and implant. Micromotion exceeding 100–150 µm disrupts fibrin scaffold organization, favoring fibrous encapsulation instead of bone anchorage [7,8]. Primary stability is influenced by bone density and implant design, while secondary stability develops through bone remodeling. Quantitative evaluation using resonance frequency analysis and insertion torque measurements provides a predictive assessment of implant success.

19. Biomechanical Testing Methods

Biomechanical assessment of osseointegration provides quantitative insights into implant–bone interfacial strength. In vitro techniques include pull-out, push-out, and torque removal tests, which evaluate interfacial shear strength [9]. In vivo methods such as resonance frequency analysis (RFA) and

periotest measurements offer non-invasive monitoring of implant stability over time. Finite element analysis (FEA) remains indispensable for simulating stress distribution and predicting failure under cyclic loading.

20. Microgap and Marginal Bone Loss

The microgap between the implant and abutment interface represents a critical zone of biological and mechanical interaction. Microgaps serve as potential sites for bacterial colonization, leading to inflammatory reactions and subsequent marginal bone resorption [10,11]. Platform switching and conical connection designs minimize micromovement and microleakage, preserving crestal bone integrity. Regular maintenance and surface decontamination protocols are essential to mitigate marginal bone loss in long-term implant function.

21. Biological Complications and Failure Modes

Although osseointegration has a high long-term success rate, biological complications such as peri-implant mucositis and peri-implantitis remain significant clinical concerns. Peri-implantitis is characterized by progressive inflammatory bone loss mediated by bacterial biofilm accumulation and host immune dysregulation [1]. Mechanical overload and residual microgaps can exacerbate inflammation, compromising the bone-implant interface. Histopathological studies reveal increased levels of pro-inflammatory cytokines (IL-1β, TNF-α) and osteoclastic activity within affected tissues [2].

22. Assessment and Imaging Techniques

Accurate assessment of osseointegration is essential for clinical decision-making and long-term prognosis. Resonance frequency analysis (RFA) provides a non-invasive quantitative measure of implant stability, expressed as the implant stability quotient (ISQ). Cone-beam computed tomography (CBCT) offers three-dimensional evaluation of bone density, cortical thickness, and implant positioning [3]. Histomorphometric analysis remains the gold standard for experimental quantification of bone-to-implant contact (BIC).

23. Patient-Related Factors

Host-related variables significantly influence osseointegration outcomes. Advanced age, smoking, and systemic diseases can impair bone metabolism and delay healing [4]. Nicotine-induced vasoconstriction and oxidative stress reduce osteoblastic activity, while chronic periodontitis alters the microbiota, predisposing to peri-implant infection. Gender-specific differences in bone turnover and hormonal regulation may also affect osseointegration dynamics.

24. Influence of Systemic Diseases

Systemic conditions such as diabetes mellitus and osteoporosis exert profound effects on osseointegration. Hyperglycemia alters collagen crosslinking and reduces angiogenic capacity, while antiresorptive therapy (bisphosphonates, denosumab) may impair bone turnover [5]. Controlled diabetic patients show comparable success rates when glycemic levels are maintained below 7% HbA1c. Inflammatory disorders and autoimmune diseases modulate cytokine profiles, necessitating individualized treatment planning.

25. Surface Decontamination and Maintenance

Maintaining a sterile and biofilm-free implant surface is critical to long-term success. Mechanical debridement using titanium curettes or air-powder abrasion removes soft deposits, while chemical agents such as chlorhexidine and citric acid eliminate microbial biofilm residues [6]. Laser-assisted decontamination (Er:YAG, diode) offers bactericidal efficacy without altering surface morphology. Regular maintenance visits and peri-implant probing are essential to detect early inflammation and prevent bone loss.

26. Regenerative and Tissue Engineering Approaches

Regenerative medicine has introduced biologically active adjuncts that enhance peri-implant bone formation. Platelet-rich fibrin (PRF), bone morphogenetic proteins (BMPs), and mesenchymal stem cell (MSC)-based scaffolds promote osteoinduction and angiogenesis [7]. Biodegradable scaffolds composed of collagen, chitosan, and hydroxyapatite provide structural support while delivering bioactive molecules in a controlled manner.

27. Smart and Sensor-Integrated Implants

Smart implant systems represent a new era in osseointegration monitoring. Embedded sensors can measure strain, temperature, and biochemical markers, transmitting data wirelessly to clinicians [8]. Piezoelectric and MEMS-based sensors are capable of detecting early signs of overloading or peri-implant inflammation. Integration with artificial intelligence enables predictive analytics, facilitating personalized post-operative management and early intervention.

28. Ethical and Clinical Considerations

Ethical considerations in implantology encompass patient autonomy, informed consent, and equitable access to advanced technologies. Digital workflows and AI-based diagnostics raise concerns regarding data privacy and algorithmic transparency. Clinicians must adhere to evidence-based protocols while ensuring that treatment recommendations align with patient safety and long-term welfare [9].

29. Future Directions

Future innovations in osseointegration are expected to converge at the intersection of materials science, biotechnology, and digital engineering. Gene-activated coatings delivering osteogenic factors, biohybrid implants integrating living cells, and nanoengineered interfaces are under active investigation [10]. Advancements in tissue regeneration, microfluidic bioreactors, and smart sensing will enable real-time biological feedback and adaptive implant behavior.

30. Conclusion

Osseointegration represents the cornerstone of implant dentistry, bridging biological processes with advanced materials engineering. Continuous innovations in surface modification, regenerative biotechnology, and digital monitoring have significantly enhanced the predictability of clinical outcomes. The integration of smart technologies and biomimetic design principles will continue to advance this field toward personalized and adaptive implant systems. Long-term success depends not only on technological progress but also on ethical stewardship, interdisciplinary collaboration, and patient-centered care.

References

1. Mombelli A, Müller N, Cionca N. The epidemiology of peri-implantitis. Clin Oral Implants Res. 2012;23(Suppl 6):67–76.
2. Klinge B, Meyle J. Peri-implant tissue destruction. Eur J Oral Sci. 2012;120(3):204–213.
3. Derhami K, et al. Evaluation of osseointegration by resonance frequency analysis. Clin Oral Implants Res. 1998;9(3):216–221.
4. Moy PK, et al. Risk factors associated with dental implant failure. J Oral Maxillofac Surg. 2005;63(9):1225–1231.
5. Fiorellini JP, Nevins ML. Impact of diabetes on dental implant outcomes. Dent Clin North Am. 2006;50(3):591–606.
6. Schwarz F, et al. Treatment options for peri-implant mucositis and peri-implantitis. Int J Implant Dent. 2015;1(1):22.
7. Dohan Ehrenfest DM, et al. Classification of platelet concentrates: from pure PRP to leukocyte- and PRF. Trends Biotechnol. 2009;27(3):158–167.
8. Puers R, et al. Smart implants for bone tissue monitoring. Biosens Bioelectron. 2014;54:1–9.
9. Beauchamp TL, Childress JF. Principles of Biomedical Ethics. Oxford Univ Press; 2013.
10. Buser D, et al. Enhanced bone apposition to chemically modified SLA titanium surfaces. J Dent Res. 2004;83(7):529–533.

References

11. Albrektsson T, Wennerberg A. The impact of oral implant surface characteristics on osseointegration: a systematic review. Int J Prosthodont. 2004;17(5):536-543.
12. Davies JE. Understanding peri-implant endosseous healing. J Dent Educ. 2003;67(8):932-949.
13. Dohan Ehrenfest DM, et al. Classification of osseointegrated implant surfaces: materials, chemistry and topography. Trends Biotechnol. 2010;28(4):198-206.
14. Brånemark PI, et al. Osseointegrated implants in the treatment of the edentulous jaw. Scand J Plast Reconstr Surg Suppl. 1977;16:1-132.

15. Adell R, et al. Long-term follow-up study of osseointegrated implants in the treatment of totally edentulous jaws. Int J Oral Surg. 1981;10(6):387-416.
16. Albrektsson T, Zarb G, Worthington P, Eriksson AR. The long-term efficacy of currently used dental implants: a review and proposed criteria of success. Int J Oral Maxillofac Implants. 1986;1(1):11-25.
17. Wennerberg A, Albrektsson T. Effects of titanium surface topography on bone integration: a systematic review. Clin Oral Implants Res. 2009;20(Suppl 4):172-184.
18. Le Guéhennec L, Soueidan A, Layrolle P, Amouriq Y. Surface treatments of titanium dental implants for rapid osseointegration. Dent Mater. 2007;23(7):844-854.
19. Davies JE. Understanding peri-implant endosseous healing. J Dent Educ. 2003;67(8):932–949.
20. Albrektsson T, et al. The long-term efficacy of currently used dental implants. Int J Oral Maxillofac Implants. 1986;1(1):11–25.
21. Dohan Ehrenfest DM, et al. Classification of osseointegrated implant surfaces. Trends Biotechnol. 2010;28(4):198–206.
22. Anselme K. Osteoblast adhesion on biomaterials. Biomaterials. 2000;21(7):667–681.
23. Meredith N. Assessment of implant stability. Int J Prosthodont. 1998;11(5):491–501.
24. Sennerby L, Meredith N. Implant stability measurements. Clin Oral Implants Res. 2008;19(8): 778–788.
25. Elias CN, et al. Biomedical applications of titanium and its alloys. J Mater Res Technol. 2019;8(1):106–110.
26. Wennerberg A, Albrektsson T. Effects of titanium surface topography on bone integration. Clin Oral Implants Res. 2009;20(Suppl 4):172–184.
27. Le Guehennec L, et al. Surface treatments of titanium dental implants. Dent Mater. 2007;23(7):844–854.
28. Kasemo B, Lausmaa J. Surface science aspects on inorganic biomaterials. CRC Crit Rev Biocompat. 1986;2(4):335–380.
29. Webster TJ, et al. Enhanced functions of osteoblasts on nanophase ceramics. Biomaterials. 2000;21(17):1803–1810.
30. Buser D, et al. Influence of surface characteristics on bone integration. J Biomed Mater Res. 1991;25(7):889–902.
31. LeGuehennec L, Soueidan A, Layrolle P, Amouriq Y. Surface treatments of titanium dental implants for rapid osseointegration. Dent Mater. 2007;23(7):844–854.
32. Daculsi G, Passuti N. Effect of the macroporosity for osseous substitution of calcium phosphate ceramics. Biomaterials. 1990;11(2):86–89.
33. Rezania A, Healy KE. Biomimetic peptide surfaces that regulate adhesion, spreading, cytoskeletal organization, and mineralization of osteoblast-like cells. Biotechnol Prog. 1999;15(1):19–32.
34. Van Noort R. The future of dental devices is digital. Dent Mater. 2012;28(1):3–12.
35. Li JP, et al. Additive manufacturing of porous titanium structures with controlled mechanical properties. J Biomed Mater Res A. 2008;85(3):661–670.
36. Schneider D, Schober F, Grohmann P, et al. Accuracy of computer-guided template-based implant placement. Clin Oral Implants Res. 2009;20(5):491–498.
37. Jacobs R, Salmon B, Codari M, Hassan B, Bornstein MM. Cone beam computed tomography in implant dentistry: recommendations. J Oral Rehabil. 2018;45(9):730–738.

38. Sadowsky SJ. The evolution of implant prosthodontics: understanding the changing paradigm. J Prosthet Dent. 2019;122(2):199–210.
39. Buser D, et al. Long-term evaluation of non-submerged titanium implants. Clin Oral Implants Res. 1997;8(2):161–172.
40. Misch CE. Contemporary Implant Dentistry. Mosby; 2014.
41. Esposito M, et al. Timing of implant loading: immediate, early, or delayed? Cochrane Database Syst Rev. 2013;3:CD003878.
42. Eriksson RA, Adell R. Temperatures during drilling for the placement of implants. J Oral Maxillofac Surg. 1986;44(1):4–7.
43. Ozan O, Turkyilmaz I, Ersoy AE. Effect of surgical techniques on implant stability. J Oral Implantol. 2007;33(3):132–138.
44. Frost HM. Bone remodeling dynamics. Springfield: CC Thomas; 1963.
45. Brunski JB. Avoid pitfalls of overloading and micromotion of intraosseous implants. Dent Implantol Update. 1999;10(10):77–81.
46. Szmukler-Moncler S, et al. Timing of loading and implant micro-motion. Clin Oral Implants Res. 2000;11(5):459–469.
47. Meredith N. Assessment of implant stability as a prognostic determinant. Int J Prosthodont. 1998;11(5):491–501.
48. Hermann JS, et al. Biological width around one- and two-piece titanium implants. Clin Oral Implants Res. 2001;12(6):559–571.
49. Quirynen M, et al. Bacterial leakage along the implant-abutment interface. Clin Oral Implants Res. 1994;5(4):239–244.
50. Mombelli A, Müller N, Cionca N. The epidemiology of peri-implantitis. Clin Oral Implants Res. 2012;23(Suppl 6):67–76.
51. Klinge B, Meyle J. Peri-implant tissue destruction. Eur J Oral Sci. 2012;120(3):204–213.
52. Derhami K, et al. Evaluation of osseointegration by resonance frequency analysis. Clin Oral Implants Res. 1998;9(3):216–221.
53. Moy PK, et al. Risk factors associated with dental implant failure. J Oral Maxillofac Surg. 2005;63(9):1225–1231.
54. Fiorellini JP, Nevins ML. Impact of diabetes on dental implant outcomes. Dent Clin North Am. 2006;50(3):591–606.
55. Schwarz F, et al. Treatment options for peri-implant mucositis and peri-implantitis. Int J Implant Dent. 2015;1(1):22.
56. Dohan Ehrenfest DM, et al. Classification of platelet concentrates: from pure PRP to leukocyte- and PRF. Trends Biotechnol. 2009;27(3):158–167.
57. Puers R, et al. Smart implants for bone tissue monitoring. Biosens Bioelectron. 2014;54:1–9.
58. Beauchamp TL, Childress JF. Principles of Biomedical Ethics. Oxford Univ Press; 2013.
59. Buser D, et al. Enhanced bone apposition to chemically modified SLA titanium surfaces. J Dent Res. 2004;83(7):529–533.